

MEMBRANE TAPE

Version No.1

Revision Date: 01/05/12

Page 1 of 2

DESCRIPTION

Membrane Tape is an extruded butyl tape designed for use for joining membranes.

KEY FEATURES

Good adhesion to a wide range of substrates.

Easy and accurate to use with little waste and no mess.

The softer composition makes this product highly conformable.

Remains flexible throughout its service life.

High tack.

Conforms to IVD Instruction Sheet No 5

USES

For joining membranes used in building and construction to prevent the passage of water and/or air, for example damp proof membranes and vapour control layers.

PERFORMANCE

| | UNIT | NOMINAL VALUE | TEST METHOD |
|---|---------------------------|---------------|------------------------|
| Dynamic Tensile Adhesion | N/cm ² | 19 | H5 |
| Dynamic Shear Adhesion | N/cm ² | 13 | H15 |
| T-Peel Adhesion to 250 micron PE membrane | N/cm | 12 | H45 |
| Specific Gravity | g/cm ³ | 1.6 | DIN EN ISO 10563 |
| Moisture Vapour Transmission Rate | g/m ² /24hr/mm | 0.16 | ISO9932 / BS ISO 15106 |
| Service Temperature Range | °C | -40 to +90 | |

H – HS Butyl Test Method

Gordleton Industrial Park,
Hannah Way, Sway Road,
Lymington, Hampshire,
SO41 8JD. UK.



T: +44 (0)1590 684400
F: +44 (0)1590 683728
E: sales@hsbutyl.com
W: www.hsbutyl.com

MEMBRANE TAPE

Version No.1

Revision Date: 01/05/12

Page 2 of 2

APPLICATION

PROPERTIES

Application temperature range: +5 °C to +40°C

Shelf life: 24 months when stored flat in original packaging in cool, dry conditions.

INSTRUCTIONS

Surface preparation: All surfaces should be clean, dry and free from frost, grease and loose materials. When cleaning contaminated substrates, HS Butyl recommend that propan-2-ol (IPA) is used and allowed to dry prior to the application of the butyl tape.

Application: Apply direct from the reel onto one surface and press sufficiently along its whole length to achieve good initial adhesion. Remove backing paper and offer other surface to the butyl tape and push firmly to seal across the joint. The use of a roller to roll the joint, using firm pressure, is recommended to get a good bond.

PACKAGING

1mm x 15mm x 25m – 20 rolls per box
 2mm x 15mm x 22.5m – 20 rolls per box
 1mm x 30mm x 10m – 24 rolls per box
 1mm x 30mm x 20m – 12 rolls per box
 1.5mm x 30mm x 10m – 12 rolls per box

2mm x 30mm x 22.5m – 10 rolls per box
 1mm x 50mm x 20m – 6 rolls per box
 1.5mm x 50mm x 10m – 6 rolls per box
 8mm bead x 6m – 22 rolls per box
 10mm bead x 4.75m – 20 rolls per box

Available colours: Black.

TOLERANCES

Rectangular sections:
 Thickness $\pm 10\%$
 Width: up to 25mm $\pm 1\text{mm}$
 26mm to 100mm $\pm 2\text{mm}$

Bead sections:
 Thickness $\pm 10\%$
 Width $\pm 10\%$

GENERAL

Membrane Tape is part of a range of butyl products for Construction & Membranes markets. For further information, please contact our Customer Care Team or visit our Website.

The information given in this product data sheet is based on laboratory tests and experience which we believe to be correct. Properties quoted are typical and do not therefore constitute a specification. In view of the wide range and variability of substrates, we would advise that our product should be tested by the user to establish suitability for its intended application. E &OE.

Gordleton Industrial Park,
 Hannah Way, Sway Road,
 Lymington, Hampshire,
 SO41 8JD. UK.



T: +44 (0)1590 684400
 F: +44 (0)1590 683728
 E: sales@hsbutyl.com
 W: www.hsbutyl.com